



PERNICKA CORPORATION

CUSTOMER NAME: A. Customer	Tested on: 11/30/2001 10:05
LOCATION: Your Town, USA	
PHONE NUMBER: 800-555-1000	P.O. #: Blanket
Contact: B.Reliable	REL. #: 001
MANUFACTURER: XYZ	LIMS #: L-9000
QTY OF PARTS: 20	
OPERATOR: DM Jernberg	SEQ #: 1
	PART #: JAN1234
INLET TEMP. Deg: 100.5C	
P (inlet) in Torr: 0.004 Torr	SERIAL #: 5678
Cal Moisture in %: 0.5000	Date Code: 9/10/2001

GASSES ANALYZED:	Volume % (1%=10,000ppm)	Limit in %	PASS?
Hydrogen	0.0000	100.0000	Yes
Helium (3)	0.0000	100.0000	Yes
Helium (4)	0.0003	100.0000	Yes
Methane	0.0020	100.0000	Yes
Water	0.1576	0.5000	Yes
Neon (20)	0.0000	100.0000	Yes
Neon (22)	0.0000	100.0000	Yes
Nitrogen	78.9415	100.0000	Yes
Carbon Monoxide	0.0000	100.0000	Yes
Oxygen	19.7359	100.0000	Yes
Argon	1.0268	100.0000	Yes
Carbon Dioxide	0.1343	100.0000	Yes
Tot. HC and Org.	0.0015	100.0000	Yes
Flouorocarbons	0.0000	100.0000	Yes
NH3	0.0000	100.0000	Yes
Krypton	0.0000	100.0000	Yes
Xenon	0.0000	100.0000	Yes

Seal Temp in Deg. C
Seal Pressure in Torr:

Internal Vol. In cc:

ISO 9002

Prebake Temperature in deg. C: 100

Time in Hrs: 16 to 24

MIL-STD 750/883

Tested on Pernicka Corp Mass Spec # 0166

Comments:

Internal Water-Vapor Content Test. Method 1018.3(1)